






Initial permeability	μ_i	25°C	1500±25%
Saturation magnetic flux density	$B_s(mT)$	25°C	530
		100°C	440
Remanence	$B_r(mT)$	25°C	210
		100°C	70
Coercivity	$H_c(A/m)$	25°C	24
		100°C	13
Core loss	$P_{cv}(kW/m^3)$	25°C	1000
	100kHz 200mT	100°C	480
Curie temperature	$T_c(^{\circ}C)$		≥285
Electrical resistivity	$\rho(\Omega\cdot m)$		3
Density	$d(kg/m^3)$		4.8×10^3



frequency

B-H

μ_i -F

