





Initial permeability	μ_i	25°C	3000±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
	1194A/m	100°C	425
Remanence	Br(mT)	25°C	100
		100°C	75
Coercivity	Hc(A/m)	25°C	15
		100°C	12
Core loss	Pcv(kW/m³)	0°C	380
		25°C	330
		100°C	350
		120°C	380



Density	d(kg/m³)	4.8×10³
Test core: Toroid(mm)		
OD : 25		
ID : 15		
H : 7.5		

